



Adsorption of Reactive Blue 19 as an Anionic Dye by PVA/CS/Triton X-100 Electrospun Nanofibers

Ali Soltani, Mohammad Hossein Sarraf Zadeh and
Abdolmajid Bayandori

EasyChair preprints are intended for rapid
dissemination of research results and are
integrated with the rest of EasyChair.

February 3, 2024

Adsorption of reactive blue 19 as an anionic dye by PVA/CS/Triton X-100 electrospun nanofibers

Ali Soltani, Mohammad Hossein Sarrafzadeh, abdolmajid Bayandouri

Abstract

Reactive dyes, due to their high molecular weight and aromatic structure, are considered more challenging pollutants than other dyes. They are highly soluble in water and are not easily removed through conventional treatment methods. The use of adsorbents to eliminate these dyes is a common approach. In this study, polyvinyl alcohol/chitosan (PVA/CS) nanofibers modified with Polyethyleneimine (PEI) were utilized as adsorbents for the removal of reactive dyes. Both polymers possess high hydrophilicity and biodegradability. The electrospinning technique, a common and cost-effective method, was employed for nanofiber fabrication. Additionally, Triton X-100 was used to facilitate the electrospinning process and enhance the quality of nanofibers.

Keywords: dye adsorption, Polyethyleneimine (PEI), chitosan (CS), polyvinyl alcohol (PVA), reactive blue19, triton X100

1.Introduction

The textile industry is one of the most important industries that is constantly advancing. The wastewater treatment of these industries is crucial due to the presence of thousands of different dyes and toxic substances. There are significant concerns regarding the presence of chemical compounds in the wastewater that exhibit high resistance to biological degradation. [1],[2] Reactive Blue 19 is a dye belonging to the group of anthraquinone dyes, and it is one of the most commonly used textile dyes after azo dyes. Various methods have been employed to remove it, such as sonochemistry, photochemistry, the use of nanoparticles, and more. These methods are used to enhance the efficiency and application of wastewater treatment containing Reactive Blue 19 dyes. [3],[4]

The high cost, resistance to removal, and the potential for recontamination in the process of removing dyes from wastewater have posed significant challenges in the field of dye removal. In this study, the surface adsorption of Reactive Blue 19 dye using electrospun nanofibers functionalized with a surfactant has been investigated. This method offers an easy and common approach to address the challenges associated with dye removal.[5] Electrospinning is a simple and inexpensive method for producing nanofibers on a nanoscale and microscale. The fabrication of electrospun nanofibers is a common method for producing fibers with various applications in industries such as pharmaceuticals, membranes, medical bandages, and water purification. [6],[7] This study utilizes a blend of two biodegradable natural polymers, polyvinyl alcohol (PVA) and chitosan, for the production of nanofibers. Both polymers are environmentally friendly and pose no risk of pollution. The inclusion of PVA alongside chitosan aids in the

electrospinning process due to its high fiber receptivity. Additionally, Triton X-100 was used to create a more uniform surface and increase the viscosity of the polymer solution, facilitating the process. [7-10]

In this work, we have chemically modified the surface of the PVA/CS/Triton X100 electrospinning the nanofibers matrix by using polyethyleneimine (PEI) to generate a positive charge on the nanofibers' surface. PEI was used as the functional compounds because of their abundant primary amine ($-NH_2$), secondary amine ($-NH-$) groups. [11],[12]

2. Experiment

2.1 Materials

Glutaraldehyde (GA 50% solution), Triton X-100, sodium carbonate (Na_2CO_3) (SigmaAldrich), Polyethyleneimine (PEI), Polyvinyl alcohol (PVA) (99% Mw = 145 kDa), Acetic acid, Hydrochloric acid (HCl 37%), Isopropyl Alcohol (Merck), Chitosan (high molecular, purity >97%) (Azin Turkan).

2.2 Fabrication of electrospun PVA/CS/TRITON-X100 composite nanofibers

To prepare the electrospinning solution, start by placing PVA 8 % w/v solution in DI water on a magnetic stirrer at a temperature of 60° C for 12 hours to allow complete dissolution. In next step CS (Chitosan) 3% w/v solution was prepared by dissolving in Acetic acid and DI water 7/3 on a stirrer for 6 hr. PVA and CS solution were mixed in order to prepare solution with PVA/CS volume ratios of 7/3 for 3 hours. After the solution has cooled down, Half of the solution separated and the other half Triton X-100 1% v/v is added to the solution, and it is placed on a stirred at room temperature for 30 min.

2.3 Electrospinning process

The PVA/CS/Triton X-100 electrospinning solution was placed into a 6 mL syringe and pumped by flowing rate of 1 mlh^{-1} . the voltage DC power was 20 kV and the distance between the tip to collector is 15 cm and the electrospinning process continues for 3 hr. In the next step, electrospinning was used to fabricate PVA/CS nanofibers without Triton X-100 under the previous electrospray conditions. After that, both electrospun nanofibers was placed in an oven for 12 hours at a temperature of 35°C to fully volatilize the solvent.

2.4 Cross-linking of nanofiber membrane by GA

Glutaraldehyde (50%) was dissolved in isopropyl alcohol with a volume percentage of 0.5%, and HCl 0.4 % (HCL/GA v/v) was used as a catalyst. the isopropyl was used as the main crosslinking solvent because it will not lead to destroy of the morphology as a non-solvent of the PVA/CS/Triton X-100 composite nanofibers.

Both nanofiber samples were immersed in a GA solution and kept for one hour to ensure complete cross-linking. Then, the nanofibers were placed inside an oven at a temperature of

60° C for 4 hours to remove any remaining solvents also enhance the resistance of the nanofibers.

2.6 Functionalization of nanofibers

Polyethyleneimine (PEI), which contains amine groups, was used to functionalize the nanofibers. To create a functionalized surface on the electrospun PVA/CS/Triton X-100 nanofibers, which were immersed in a solution containing 15 mL of PEI and 0.2 mL of sodium carbonate for 2 hours. Then, the functionalized nanofibers are washed three times with DI water to remove any excess materials completely. In the final step, the nanofibers are placed inside an oven at a temperature of 60° C for 12 hours to dry them and ensure they have the necessary strength

References

- Congjing Cui, S. S. (2021). Electrospun chitosan nanofibers for wound healing application. *Engineered Regeneration*. Daneshvar N., S. D. (2003). Photocatalytic degradation of azo dye acid red 14 in water: investigation of the effect of operational parameters. *Photochem. Photobiol. A: Chem.* 157, 111- .
- Huang ZM, Z. Y. (2003). Fabrication of porous electrospun nanofibres. *Compos Sci Technol*;63:2223–53.
- M, M. K. (2016). Removal of reactive blue 19 from aqueous solutions using NiO nanoparticles: equilibrium and kinetic studies, J. Desalin. *Water Treat.* 57 (42), 20037-2004 .
- Nasir Khan M. A., S. M. (2015). Removal of reactive blue 19 dye by sono, photo and sonophotocatalytic oxidation using visible light. *Ultrasonic. Sonochem.* 26, 370-37 .
- Qinghua Wua, X. L. (2022). Preparation of aminated porous polyacrylonitrile nanofibers as adsorbent for methyl orange removal. *The Royal Society of Chemistry*.
- S., S. H. (2006). Ozone Pre- Oxidation of a Textile Industry Wastewater for Acute Toxicity Removal. *Global NEST J.* . Sarmadi N., G. M. (2017). New technologies in the synthesis of nanostructures used in wastewater treatment- A review. *J. Environ .*
- Satinderpal Kaur a, b. S. (2012). Influence of electrospun fiber size on the separation efficiency of thin film. *Journal of Membrane Science*.
- Science, D. Y. (2004). Spinning continuous fibers for nanotechnology. *Material science*.304:1917–9.
- Y Z Zhang1, 2. Y.-M. (2006). Fabrication of porous electrospun nanofibres. *Compos Sci Technol* ;63:2223–53.
- Yong-Tang Jia a, d. J. (2007). Fabrication and characterization of poly (vinyl alcohol)/chitosan . *Journal of Membrane Science*.
- Zhixiang Cui1, 2. |. (2016). Electrospinning and crosslinking of polyvinyl alcohol/chitosan . 1.